



TRUCCSA

Revestimientos y Morteros especiales para la Construcción

Atención al Cliente

968 081 080

TECHNICAL DATA SHEET

LAVADO PLUS

OC - CSIV - W1



 TRUCCSA SIGLO XXI
 05
 UNE EN 998-1

COMPOSITION

30% + 1% White cement
 Portland type CEM I
 52,5 R UNE 197-1

65% + 1% of selected
 aggregates.

5% of additives.

CHARACTERISTICS

Excellent workability. High
 yield. Very good adherence
 to sound substrates.
 Can be applied directly
 onto the surface.

Yield: 1,8 Kg/m² and per
 mm of thickness.

COLOUR RANGE

White
 Special colors are
 available on request.

SUBSTRATES

Prefabricated cement
 blocks, ceramic bricks and
 concrete.

CONSERVATION

Store in a dry place.

STORAGE

Shelf life is approximately
 6 months from date of
 manufacture if stored in
 unopened original packing
 in dry conditions.

PACKAGING

25 kgs. 3 ply paper-plastic-
 paper sacks.

Shrink-wrapped pallets of
 1.400 kg.(56 sacks)

DESCRIPTION

A mortar made from cement, selected aggregates and additives, ready to be mixed with water, for manual or machine application. For waterproofing and decorating façades and interiors. Sponge float finish or trowelled finish.

HOW TO USE

Mix with 26% water until an homogenous blend is achieved. Wait for several minutes before applying. Mix manually or mechanically. Apply a minimum thickness of 8mm of the mortar to the base using a steel trowel. The washing process should be carried out using a slightly moist sponge. A maximum of 1 to 2 hours should be allowed between application and washing. The time required may vary according to climatological conditions.

PRECAUTIONS

The base should be clean, free of loose parts, paints and grease.
DO NOT APPLY ONTO PLASTER.

Do not apply at temperatures below +5° C or above +35° C.

The product must not be applied to frozen or thawing supports. If the coating must be applied in adverse weather conditions, it is essential to protect both the working area and finish before and after application. For further information consult Material Safety Data Sheet (MSDS)

TECHNICAL DATA

	Value	Regulation
Reaction to fire	A1(Incombustible)	UNE-EN 13501-1:2002
Adhesion	0,8 N/mm ² – FP:B	UNE-EN 1015-21:2003
Resistance to flexion	2,9 N/mm ²	UNE-EN 1015-11:2000
Resistance to compression	7,8 N/mm ²	UNE-EN 1015-11:2000
Capillary absorption coefficient	0,3 Kg/m ² *min ^{0.5}	UNE-EN 1015-18:2003
Permeabilidad al vapor de agua	μ 10,88	UNE-EN 1015-19:1999
Water permeability	0,5 ml/cm ²	UNE-EN 1015-21:2003
Dry Bulk density	1768 Kg/m ³	UNE-EN 1015-10:2000

Laboratory values obtained under standard conditions

CE according to UNE-EN 998-1:2003

Clasificación: **OC - CSIV - W1**