



TRUCCSA

Revestimientos y Morteros especiales para la Construcción

Atención al Cliente

968 081 080

TECHNICAL DATA SHEET



 TRUCCSA SIGLO XXI
 07
 UNE EN 998-1

COMPOSITION

17% + 1% White cement
 Portland type CEM I
 52,5 R UNE 197-1

80% + 1% of selected
 aggregates.

3% of additives.

CHARACTERISTICS

Excellent workability. Very
 good adherence to sound
 substrates.
 Can be applied directly
 onto the surface. Good
 mechanical resistance.

Yield: 1,8 Kg/m² and per
 mm of thickness.

COLOUR RANGE

White
 Special colors are
 available on request.

SUBSTRATES

Prefabricated cement
 blocks, ceramic bricks and
 concrete.

CONSERVATION

Store in a dry place.

STORAGE

Shelf life is approximately
 12 months from date of
 manufacture if stored in
 unopened original packing
 in dry conditions.

PACKAGING

25 kgs. 3 ply paper-plastic-
 paper sacks.

Shrink-wrapped pallets of
 1.400 kg.(56 sacks)

LAVADO

OC - CSIV - W2

DESCRIPTION

A mortar made from cement, selected aggregates and additives ready to be mixed with water, for manual or machine application.
 To prepare substrates for subsequent painting.

HOW TO USE

Mix the product with 22% water until an homogenous blend is achieved.
 Apply the mortar using a trowel to minimum thickness of 8 mm. The mortar may also be applied with a spray machine. Smooth with a trowel.

PRECAUTIONS

The base should be clean, free of loose parts, paints and grease.
DO NOT APPLY ONTO PLASTER.
 Do not apply at temperatures below +5° C or above +35° C.
 The product must not be applied to frozen or thawing supports. If the coating must be applied in adverse weather conditions, it is essential to protect both the working area and finish before and after application.
 For further information consult Material Safety Data Sheet (MSDS)

TECHNICAL DATA

	Value	Regulation
Reaction to fire	A1 (fireproof)	UNE-EN 13501-1:2002
Adhesion	≥ 0,3 N/mm ²	UNE-EN 1015-21:2003
Resistance to adherence	B	UNE-EN 1015-21:2003
Resistance to compression	≥ 3,7 N/mm ²	UNE-EN 1015-11:2000
Water absorption coefficient	W2	UNE-EN 1015-18:2003
Water vapour permeability	μ ≤ 10	UNE-EN 1015-19:1999
Water permeability	≤ 1 ml/cm ³	UNE-EN 1015-21:2003

Laboratory values obtained under standard conditions

CE according to UNE-EN 998-1:2018
 Clasification: **OC - CSIV - W2**